



HB42[®] All-in-One | SEALANT & ADHESIVE

GEV EC1 Approved

06/06/18 - Vs.1

TECHNICAL DATA SHEET HB42 SEALANT & ADHESIVE Clear / 290ml cartridge

Sealant & Adhesive
Interior & Exterior
Works in wet (even underwater)
Flexible (Non shrinking)
Durable
Can be over-painted
Solvent free
Suitable as mirror adhesive
Bonds to almost anything (incl. lead)
Odourless
EC1 rated, very low VOC's.
Food safe

Conforms to ISO 11.600 F25 HM classification for building construction
Conforms to EC No. 1935/2004 for materials intended to come into contact with food.
GEV Approved no: 4408/19.02.10: EC1 Classification for very low emissions
Hilton Banks Ltd: GEV Member OM-064

Uses:

Sealing joints around sanitary fixtures
Sealing joints around windows & doors (can be over-painted)
Weatherproofing joints
For use in glazing systems
Fixing skirting, panels, windows, thresholds, insulation materials
Fixing mirrors
Seals & bonds glass
Bonds & seals wood, stainless steel, aluminium, porcelain, UPVC, coated metal, polystyrene
May be used safely in food preparation areas

Application:

Ensure surfaces are clean & dust free. Cut the cartridge seal and screw on the nozzle, having cut to required size. Using a skeleton gun, apply sealant into the gap or joint to provide a good solid fill. If



HB42[®] All-in-One | SEALANT & ADHESIVE

GEV EC1 Approved

required place masking tape along the edges, removing within 10 minutes of application. Use a sealant finishing tool or a stick wetted with soapy water to achieve smooth finish. For bonding applications, apply in vertical lines at a distance of 30cm. Support the application for 24 hours until full curing occurs. If painting, use a water-based paint.

Health & Safety

Contains Bis – (1.2.2.6.6-pentamethyl-4-piperidyl) sebacate, N-(3-(trimethoxysilyl)propyl)ethylenediamine, N-(3-(dimethoxymethylsilyl)propyl)ethylenediamine. May produce an allergic reaction. See safety data sheet, available on www.hiltonbanks.com

Limitations

HB42 Sealant & Adhesive is not recommended for use on PE, PP, Teflon, wax, neoprene and bituminous surfaces. Not suitable for aquaria. Not paintable with alkydresin paint. Not suitable for sealing insulation glass or in contact with PVB foil or coat glass. On porous surfaces such as concrete, a primer is recommended. HB42 Clear sealant is not UV resistant or suitable for use on natural stone. It is the users' responsibility to determine suitability, tests prior to application are recommended. Store between +5 & +25 degrees centigrade in cool dry conditions.

Liability

The information given is the result of tests and experience and is believed to be accurate & reliable. As Hilton Banks Ltd cannot know all the uses that HB42 Sealant & Adhesive may be put to or control how it is applied, it is the responsibility of the user to determine suitability of use.

TECHNICAL DATA

CLEAR

Slump ISO 7390	mm	<2
Density	g/ml	1,06
Skin forming time 23 °C/55%RH	min	10
Max movement allowed ISO 9040	%	25
Temperature resistance after curing	°C	-40- +100
Shrinkage		nil
Curing (24 hours) 23 °C/55%RH	mm	2
Mechanical properties		
2mm film		
Hardness, Shore A DIN 53505		45
Modulus, 100% DIN 53504	MPa	1,15
Tensile strength DIN 53504	MPa	2,40
Elongation at break DIN 53504	%	250



HB42[®] All-in-One | SEALANT & ADHESIVE

GEV EC1 Approved

Hilton Banks Ltd, 74 Oldfield Road, Hampton, Middx, TW12 2HR
Tel: 020 8979 8284 www.hiltonbanks.com

